



NovaCoat AQ-630

All-Purpose Work-and-Turn Coating

Description

NovaCoat AQ-630 was formulated to be an all-purpose work-and turn-coating for use in sheetfed and flexographic applications. In most applications, it can be used as a 2-sided commercial coating. It IS recommended to be recoatable. TEST BEFORE USING!

Features

- * Excellent recoatability.
- * Good gloss.
- * Excellent flow and leveling.
- * Fast dry.

Directions

MIX BEFORE USE. Check viscosity. Add 1% water or 50/50 blend of Water/IPA under agitation to reduce coating viscosity 4" # 3 Zahn. DO NOT FREEZE.

Technical Specifications

<i>Flash Point (°F TCC)</i>	> 200
<i>pH</i>	8.0 – 8.5
<i>Weight/Gallon</i>	8.76
<i>Gloss</i>	10-30 points over stock, depending on porosity
<i>Rub Resistance</i>	7/10
<i>Slip (face to face)</i>	18-22 degrees
<i>COF (face to face)</i>	.32-.40
<i>Block Resistance (face to face)</i>	Pass 120 F x 24 hr, 100% RH
<i>Gluing, Stamping</i>	Suitable with some glues and foils. TEST FIRST!
<i>UV Primer</i>	Suitable with some UV coatings. TEST FIRST!
<i>Viscosity (#3 Signature Zahn Cup)</i>	18-20" @ 77 F
<i>Inks</i>	Use recoatable inks only
<i>Dilution</i>	1% water will reduce viscosity 4" #3 Zahn
<i>Wet Film Weight</i>	3-6 micron
<i>Percent Solids</i>	40.0 +/- 2
<i>Shelf Life</i>	12 months, 6 after opening
<i>Freeze/Thaw Stability</i>	1 cycle
<i>Drying</i>	Pile 105 F 1st side, 95F 2nd side
<i>Clean-up</i>	Warm water. Water + ammonia for dried coating.

Rev. 2/8/2008

Disclaimer: Unless otherwise restricted by applicable law, nothing contained in this literature shall be deemed a representation or warranty of any kind, either expressed or implied. See the Material Safety Data Sheets (MSDS) for this product for safety information prior to use.