



UV MATTE COATING

DESCRIPTION:

NOVACURE-7100 is a 100% reactive overprint matte coating and contains no solvents. It can be utilized in roller, blanket, narrow web, and flexo applications. Gloss readings are < 25 white and < 35 black on leneta card with low viscosity and stable distribution. It is versatile and consistent and will not bind up on equipment. It has a smooth matte finish with excellent rub resistance. It also has excellent shelf stability and will not body up. No more wasted product!

INK HANDLING:

MIX WELL BEFORE USE. Direct skin contact to UV coatings is the primary route of exposure and irritation. Therefore, it is recommended that all personnel handling UV products wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where coating may be splashed. If coating does come in contact with skin, wipe it off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water. Consult the Safety Data Sheets for further instructions and warnings.

STORAGE:

Store tightly covered at temperatures between 65-90°F. Coating taken from the press should not be returned to the original container. Store separately to avoid contamination.

FEATURES:

- Low Viscosity
- Excellent Rub Resistance
- Flexible
- Low Gloss <35 black, <25 white leneta card
- Fast Cure
- Stampable
- Glueable
- Imprintable

APPLICATIONS:

- Roller
- Blanket
- Narrow Web
- Flexo
- Anilox
- In-Line
- HP Indigo

TECHNICAL SPECIFICATIONS:

Flash Point (*F TCC)	> 200
Specific Gravity	1.10
Color	Colorless
Solids	100%
Gluing, Stamping	Test First due to variety of glues and foils
Viscosity	18-22" #3 Zahn @ 77°F
Cure Speed	Up to 250 feet per minute with a 300 watt bulb
Flammability	No
Gloss	< 35° black, <25° white @ 60°F leneta card reading
Shelf Life	12 months

Nova Pressroom Products, LLC
1663 McDuff Ave N
Toll-Free: 866-443-5811
Tel: 904-292-2554
Fax: 904-389-6999
www.novapressroom.com

VERIFICATION OF SUITABILITY: SDS'S ARE AVAILABLE ONLINE AT NOVAPRESSROOM.COM OR CALL 904-292-2554 X22.

After press/job set-up is complete, inspect a portion of the printed web for all applicable and specified properties. These properties include but are not limited to: cure, adhesion, mar and rub resistance, product resistance, gloss, and coefficient of friction. These tests should be performed prior to beginning the full production run.

*Performance specifications will vary depending on substrate, ink used, lamps, and coating film weight.

Disclaimer: Unless otherwise restricted by applicable law, nothing contained in this literature shall be deemed a representation or warranty of any kind, either expressed or implied. See the Safety Data Sheets (SDS) for this product for safety information prior to use.

SIZES AVAILABLE: **5 gal, 55 gal, or 275 gal**