



## UV DIGITAL HIGH GLOSS LOW VISCOSITY

### DESCRIPTION:

NOVACURE-7200 is a 100% reactive, low viscosity, overprint varnish for digital inks. It can be utilized in roller, blanket, narrow web, flexo, anilox, and in-line applications. IR pretreatment is not mandatory in all cases; please test first. It adheres to most digital inks, and it also exhibits high gloss, rub resistance, and fast cure.

### INK HANDLING:

**MIX WELL BEFORE USE.** Store out of direct sunlight, and practice good housekeeping to avoid contamination. Direct skin contact to UV coatings is the primary route of exposure and irritation. Therefore, it is recommended that all personnel handling UV products wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where coating may be splashed. If coating does come in contact with skin, wipe it off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water. Consult the Material Safety Data Sheets for further instructions and warnings.

### STORAGE:

Store tightly covered at temperatures between 65-90°F. Coating taken from the press should not be returned to the original container. Store separately to avoid contamination.

### FEATURES:

- High Gloss
- Fast Cure
- Low Odor
- Low Viscosity
- Excellent Adhesion

### APPLICATIONS:

- Roller
- Blanket
- Narrow Web
- Flexo
- Anilox
- In-Line

### TECHNICAL SPECIFICATIONS:

Flash Point (*F TCC)	> 200
Specific Gravity	1.32
Color	Colorless
Solids	100%
Gluing, Stamping	Test First due to variety of glues and foils
Viscosity	90-115 CPS @ 60 RPM and 77°F/23°C
Cure Speed	Up to 250 feet per minute with a 300 watt bulb
Flammability	No
Gloss	90-99
Shelf Life	6 months

Nova Pressroom Products, LLC  
 1663 McDuff Ave N  
 Toll-Free: 866-443-5811  
 Tel: 904-292-2554  
 Fax: 904-389-6999  
[www.novapressroom.com](http://www.novapressroom.com)

### VERIFICATION OF SUITABILITY: SDS'S ARE AVAILABLE ONLINE AT NOVAPRESSROOM.COM OR CALL 904-292-2554 x22.

After press/job set-up is complete, inspect a portion of the printed web for all applicable and specified properties. These properties include but are not limited to: cure, adhesion, mar and rub resistance, product resistance, gloss, and coefficient of friction. These tests should be performed prior to beginning the full production run.

\*Performance specifications will vary depending on substrate, ink used, lamps, and coating film weight.

Disclaimer: Unless otherwise restricted by applicable law, nothing contained in this literature shall be deemed a representation or warranty of any kind, either expressed or implied. See the Material Safety Data Sheets (MSDS) for this product for safety information prior to use.

SIZES AVAILABLE: 1 gal, 5 gal, 55 gal, or 275 gal