



**MULTI-PEARL UV GLOSS**

**DESCRIPTION:**

NOVACURE-7403 is a 100% reactive UV multi-pearl gloss coating and can be used as a overprint for visual effect on paper and board substrates. NOVACURE-7403 is a low viscosity product and the textured effect can be increased based on volume of coating applied. It is formulated for fast cure, gloss and versatility. NOVACURE-7403 derives a multi-pearl sparkle effect. This product must be mixed prior to every use.

Pearl coatings include a dry small micron size material that can become abrasive to anilox rollers, blades, pumps and other equipment parts. It is end users responsibility to do all prior testing and to monitor for damage. Wider and shallow anilox cells are required for best distribution.

**INK HANDLING:**

**MIX WELL BEFORE USE.** Direct skin contact to UV coatings is the primary route of exposure and irritation. Therefore, it is recommended that all personnel handling UV products wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where coating may be splashed. If coating does come in contact with skin, wipe it off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water. Consult the Safety Data Sheets for further instructions and warnings.

**STORAGE:**

Store tightly covered at temperatures between 65-90°F. Coating taken from the press should not be returned to the original container. Store separately to avoid contamination.

**FEATURES:**

- Multi-pearl sparkle effect
- Fast cure
- Good rub resistance
- Versatile use
- Low viscosity

**APPLICATIONS:**

- Roller
- Anilox
- Flexo
- Narrow Web
- Screenprint

**TECHNICAL SPECIFICATIONS:**

Flash Point (°F TCC)	> 200
Specific Gravity	1.08
Color	Colorless
Solids	100%
Gluing, Stamping	Test First due to variety of glues and foils
Viscosity	180-220 @ 60 RPM and 77°F/23°C
Cure Speed	250 feet per minute with a 300 watt bulb
Flammability	No
Shelf Life	12 months

Nova Pressroom Products, LLC  
1663 McDuff Ave N  
Toll-Free: 866-443-5811  
Tel: 904-292-2554  
Fax: 904-389-6999  
[www.novapressroom.com](http://www.novapressroom.com)

**VERIFICATION OF SUITABILITY: SDS'S ARE AVAILABLE ONLINE AT NOVAPRESSROOM.COM OR CALL 904-292-2554 x22.**

After press/job set-up is complete, inspect a portion of the printed web for all applicable and specified properties. These properties include but are not limited to: cure, adhesion, mar and rub resistance, product resistance, gloss, and coefficient of friction. These tests should be performed prior to beginning the full production run.

\*Performance specifications will vary depending on substrate, ink used, lamps, and coating film weight.

Disclaimer: Unless otherwise restricted by applicable law, nothing contained in this literature shall be deemed a representation or warranty of any kind, either expressed or implied. See the Safety Data Sheets (SDS) for this product for safety information prior to use.

SIZES AVAIL: 5 gal, 55 gal, or 275 gal