



## AQ-7065

*Aqueous High Rub Matte Coating*

### Description

NovaCoat AQ-7065 is formulated to have a matte finish. It can be used in 1 or 2-sided coating for use in sheetfed and flexographic applications. AQ-7065 will provide extra rub/scratch resistance and good block resistance.

### Features

- Matte Finish
- Good Rub Resistance
- Good Flow and leveling

### Directions

Mix before use and check viscosity. Add 1% water or 50/50 blend of Water/IPA under agitation to reduce coating viscosity 3" # 3 Zahn

### Technical Specifications

<i>Flash Point (°F TCC)</i>	> 200
<i>pH</i>	8.2 - 9.2
<i>Weight/Gallon</i>	8.76
<i>Gloss</i>	Matte finish
<i>Rub Resistance</i>	8/10
<i>Slip (face to face)</i>	16 - 22 degrees
<i>Block Resistance (face to face)</i>	Pass 120 F x 24 hr, 100% RH
<i>Gluing, Stamping</i>	N/A
<i>UV Primer</i>	N/A
<i>Viscosity (#3 Signature Zahn Cup)</i>	17-20" @ 77 F
<i>Inks</i>	Use recoatable inks only
<i>Dilution</i>	1% water will reduce viscosity 3" #3 Zahn
<i>Wet Film Weight</i>	0.9 – 1.1 lbs per 1000 square feet
<i>Percent Solids</i>	40.0 +/- 2
<i>Shelf Life</i>	12 months, 6 after opening
<i>Freeze/Thaw Stability</i>	1 cycle
<i>Drying</i>	Pile 105 F 1st side, 95F 2nd side
<i>Clean-up</i>	Warm water. Water + ammonia for dried coating

Disclaimer: Unless otherwise restricted by applicable law, nothing contained in this literature shall be deemed a representation or warranty of any kind, either expressed or implied. See the Safety Data Sheets (SDS) for this product for safety information prior to use. Performance characteristics will vary depending on type of substrate, coating film weight and type of ink / coverage.

---

#### Nova Pressroom Products LLC

1663 North McDuff Avenue, Jacksonville, FL 32254 | PO Box 2700, Jacksonville, FL 32203  
toll-free: 866.443.5811 tel: 904.292.2554 fax: 904.292.2665 [www.novapressroom.com](http://www.novapressroom.com)