



## NovaCoat A170MF/7

*Aqueous Gloss Coating*

### Description

NovaCoat A170MF/7 is formulated for application on paper and paperboard with in-line blanket coaters, flexo presses and flexo/gravure type coaters. It has very good rub resistance.

### Features

\* Very good rub resistance.

### Directions

Mix before use and check viscosity. Add water or 50/50 blend of Water/IPA under agitation to reduce coating viscosity.

### Technical Specifications

<i>Flash Point (°F TCC)</i>	> 200
<i>pH</i>	8.0 – 9.0
<i>Weight/Gallon</i>	8.76
<i>Gloss</i>	15-35 points over stock, depending on porosity
<i>Rub Resistance</i>	8/10
<i>Slip (face to face)</i>	21-24 degrees
<i>COF (face to face)</i>	.32-.36
<i>Block Resistance (face to face)</i>	Pass 12F x 24 Hr, 100% RH
<i>Gluing, Stamping</i>	Suitable with some glues and foils. TEST FIRST!
<i>UV Primer</i>	
<i>Viscosity (#3 Signature Zahn Cup)</i>	20-25" #3 (Signature brand)
<i>Inks</i>	Coatable inks only
<i>Dilution</i>	1% water will reduce viscosity 2" #2 Zahn
<i>Wet Film Weight</i>	3-6 micron
<i>Percent Solids</i>	45.0 +/- 2.0
<i>Shelf Life</i>	12 months, 6 after opening
<i>Freeze/Thaw Stability</i>	1 cycle
<i>Drying</i>	Pile 105F 1st side, 95 F second
<i>Clean-up</i>	Warm water or water + ammonia

Rev. 2/10/2010

Disclaimer: Unless otherwise restricted by applicable law, nothing contained in this literature shall be deemed a representation or warranty of any kind, either expressed or implied. See the Material Safety Data Sheets (MSDS) for this product for safety information prior to use.